

079200 JOINT SEALERS

1. Do not use and misuse the word "caulk". Such materials generally consist of oil-based materials and are no longer used for glazing or as a sealant in masonry joints or other exterior wall joints.
2. The use of 2-part polyurethane or silicone-synthetic rubber type sealant is preferable. Determine which particular sealant type is best suited to each individual application. Specify pourable urethane-based sealants for construction joints in traffic bearing locations such as concrete walks, patios, steps and similar locations. Specify mildew-resistant silicone sealant for sanitary applications such as in food preparation areas and toilet rooms.